



# Product Data Sheet

## 280

### General Product Description

	Min	Max	Target
%-325 Mesh (44 Micron)	95	98	<input type="checkbox"/>
%Carbon (LOI)	96	100	<input type="checkbox"/>

**Type:** Sri Lankan

### Typical Analysis

*(U.S. Standard Test Sieves)*

%Carbon (LOI)	96.08
%+325 Mesh (44 Micron)	2.63
%-325 Mesh (44 Micron)	97.37
Surface Area m2/g	4.11

### Test Methods

CARB	E4-1
MT	E3-5B
SA	E3-6
SC	E2-2

The PDS lists percentages which are only guaranteed following specific agreement between Asbury and the customer. They are listed here only to indicate approximate physical and chemical analysis. Purchasers should thoroughly test and independently verify satisfactory results before application. The user assumes the risk and liability for loss, damage, or injury arising from the application of the goods furnished.

UNCONTROLLED DOCUMENT: Prior to placing an order based on this PDS, contact the Asbury Sales Department to confirm that the information contained herein is current.

**Revision Level:** REVISION 3

**Revision Date:**

7/14/1999

### **Asbury Graphite Mills, Inc.**

PO Box 144 405 Old Main St.

Asbury, New Jersey 08802

**Tel:** (908) 537-2155 **Fax:** (908) 537-2108 **http://** [www.asbury.com](http://www.asbury.com)