



Product Data Sheet Nano25

General Product Description

	Min	Max	Target
%Carbon (LOI)	97		<input type="checkbox"/>

Type: Surface Enhanced Flake Graphite

Typical Analysis

(U.S. Standard Test Sieves)

%Carbon (LOI)	97.54
%Moisture	1.28
Surface Area m2/g	172.08

Test Methods

%Sulfur	E4-9
Carbon	E4-1
Microtrac	E3-5B
Moisture	E4-7
Surface Area	E3-9

The PDS lists percentages which are only guaranteed following specific agreement between Asbury and the customer. They are listed here only to indicate approximate physical and chemical analysis. Purchasers should thoroughly test and independently verify satisfactory results before application. The user assumes the risk and liability for loss, damage, or injury arising from the application of the goods furnished.

UNCONTROLLED DOCUMENT: Prior to placing an order based on this PDS, contact the Asbury Sales Department to confirm that the information contained herein is current.

Revision Level: ISSUE

Revision Date:

7/16/2012

Asbury Graphite Mills, Inc.

PO Box 144 405 Old Main St.

Asbury, New Jersey 08802

Tel: (908) 537-2155 **Fax:** (908) 537-2108 **http://** www.asbury.com